

CLASSIC MALE WEISS



Washable interior wall paint in accordance with DIN EN 13300

USE

Interior walls and ceilings (ceilings, plaster, plasterboard, brickwork, ...), product particularly suitable for **direct applications on plasterboard surfaces**.

PROPERTY'

- Washable water-based wall paint compliant with DIN EN 13300.
- Excellent covering power (**Class 1**)
- Suitable for direct applications on plasterboard surfaces (without primer, to be checked according to the type of support)
- Odorless.
- Hygiene certificate **TUV**: absence of harmful substances (heavy metals, organic compounds, plasticizers) during and after application.
- Quality **ELF** (Emissions- and solvent-free): without plasticizers, without solvents and low emissions (the ELF label is awarded to paints that contain a reduced solvent content or are free of solvents).
- Compliant with internal emissions tests **Indoor Air Comfort Gold (IAC Gold) by Eurofins**
- Complies with the requirements set by the certifications **Leed v4.1, Breeam, Well, CAM Edilizia (DM 23 June 2022, n° 256)**

CHARACTERISTICS

Composition: based on synthetic resins in aqueous emulsion, pigments and selected fillers. **Density:** approx. 1,590 kg/l **Physical parameters according to EN 13300:**

Wet abrasion	class 3	(≥ 20 -m < 70 -m at 200 cycles)
Covering power	class 1 (with a yield of approximately 5-6 m ² /l)	($\geq 99.5\%$) S ₁
Granulometry	end	(< 100 -m)
Emissions	ELF	(free from solvents, plasticizers and emissions)
I wait	G30paque	(< 10 GU 85°) (approx. 1.5)

EU limit value for VOC content: Cat. A/a: 30 g/l 2010.

This product contains a maximum of 1 g/l VOC.

Colors: White / Base DU1 : *The product can be coloured in pastel shades with the colouring pastes of the Acomix system.*

Packaging: White/Base DU1 in the following formats: 1, 5 and 12.5 litres.

Conservation: Store the product in its original packaging, tightly closed and in a dry, cool place, away from frost.

INSTALLATION

Application: by brush, roller and spray (also airless: pressure: approx. 150 bar - nozzle: starting from 0.017 inch - 60 mesh filter - angle 40° - 80°).

Dilution: 20 to 30% by volume with water.

Conditions of application: Application and drying must take place in temperature conditions between +5°C and +30°C and with relative humidity lower than 85%

Theoretical consumption: about 150 - 200 ml/m² by hand.

Practical yield: about 10 - 12 m²/l per coat. Yield may vary depending on the roughness, porosity and absorption characteristics of the substrates and the application system used.

Drying (at 23°C and 50% RH):

- Repaintable: after approximately 4 - 5 hours.
- Final drying: after approximately 2 or 3 days.

CLASSIC MALE WEISS

APPLICATION SYSTEMS

The application system and preparation of the substrates must be evaluated and chosen based on the current state and the conditions to which the substrate itself will be exposed.

Supports: the substrates must be healthy, clean, dry and free from saline efflorescence, mold, algae or fungi. They must not be crumbling or have detached parts. To clean surfaces contaminated by microorganisms, use Fungimos.

Preparation of the supports: clean the surfaces and consolidate the crumbling ones. Repair the surface defects by applying suitable products from the Polyfilla Pro line. Do not apply the product on new plasters for at least 4 weeks. In the case of patched surfaces for which it is necessary to even out the surface texture, it is possible to apply a coat of Fassaden Putzfüller following the instructions given in the respective Technical Data Sheet.

New and highly absorbent surfaces:

- Apply with a brush, as a preparatory coat, one coat of Classic Malerweiss diluted 50% by volume with water.
- Finally, apply two coats of Classic Malerweiss diluted 20 to 30% by volume with water depending on the application system used.

Surfaces already painted with washable or breathable finishes:

- Directly apply two coats of Classic Malerweiss diluted 20 to 30% by volume with water depending on the application system used.

Recommendations:

- For some types of plasterboard panels, with specific characteristics and compositions, for example anti-humidity, fireproof, high density panels, etc. it is recommended to carry out a preliminary sampling of the cycle to verify the optimal adhesion to the substrate.

SECURITY INFORMATION

For information on the correct disposal, storage and handling of the product, please consult the relevant Safety Data Sheet.

All technical information contained herein is indicative. For further information, please consult our Technical Assistance service.

Herbalis is a trademark of: **AKZO**

NOBEL COATINGS SpA SALES

OFFICE and

ADMINISTRATIVE HEADQUARTERS:

28053 Castelletto Sopra Ticino (NO) Via

Pietro Nenni, 14

Tel. 0331 916611



www.herbol.it

customerservice@akzonobel.com

The effectiveness of our products and systems is based on years of practical experience and research conducted in our laboratories. We guarantee that the quality of work carried out with our products meets the suitability requirements set by Akzo Nobel Coatings SpA, provided that all instructions given by us are correctly followed and the work has been carried out in a skillful and professional manner. In the event that the final result has been adversely affected by circumstances beyond our control, any and all liability is expressly excluded and declined. The purchaser is responsible for checking whether the products delivered are suitable for the intended use. We reserve the right to change the content of this document without prior notice. As soon as a new version of this technical data sheet is available, it will no longer be valid.