



## TITANIUM

Breathable anti-mold water-based paint



<b>Description</b>	Wall paint formulated with raw materials that fall within the Class A + regulations, these give the product excellent breathability, coverage and whiteness. The product is characterized by an excellent opacity and is able to mask the defects present on the support.
<b>Composition</b>	Based on acetovinyl resins and selected pigments in aqueous dispersion.
<b>Specific weight</b>	1,600 - 1650 kg / lt
<b>Surrender</b>	8 - 10 sqm / l per coat
<b>Percentage by weight of the dry resin on the total dry</b>	4% +/- 1
<b>Coverage</b>	Excellent after complete drying
<b>Filling</b>	Great
<b>Appearance of the film</b>	Opaque
<b>Film thickness</b>	75 - 85 microns in both coats.
<b>storage</b>	In tightly closed package
<b>Use</b>	For internal walls
<b>Application</b>	Brush or short-haired roller
<b>Dilution</b>	30 - 45% by volume with water
<b>Temperature of application</b>	10-35C ° relative humidity max. 85%
<b>Drying at 25 ° C</b>	Dry: 3 - 5 hours depending on the environmental conditions.
<b>Over application</b>	5 - 6 hours

<b>Color</b>	White
<b>Pack of sale</b>	4 lt - 14 lt
<b>Cleaning tools</b>	Water and detergent

---

#### **Preparation of the support**

##### **NEW WALLS:**

- Carry out a thorough sanding and brush the substrate, to remove dirt and inconsistencies present.
- Apply two coats of SFERA according to the instructions above.

##### **ALREADY PAINTED WALLS:**

- Eliminate any inconsistencies in the substrate by carefully brushing and cleaning the substrate.
- Check the adhesion of the old paints, if necessary remove them with the help of a wet sponge, scraper, brush, etc.
- Apply two coats of SFERA according to the instructions above.

#### **NB**

**Application on walls with washable film-forming paints is not recommended.**

---

#### **SPECIFICATION ITEM (for tenders and estimates)**

<b>Description</b>	Wall paint formulated with raw materials that fall within the Class A + regulations, these give the product excellent breathability, coverage and whiteness. The product is characterized by an excellent opacity and is able to mask the defects present on the support.
<b>Specific weight</b>	1,600 - 1,650 kg / lt
<b>Percentage by weight of the dry resin on the total dry</b>	4% +/- 1

---

#### **Warnings**

- The substrate temperature must be at least 3C ° higher than the condensation temperature.
- Apply the product with temperatures ranging from 10C ° -35C ° and with a relative humidity of max. 85%
- If the product is applied indoors, a continuous air exchange is required, so that the water vapors escape.
- Apply the product on a carefully treated surface.

- The yield may vary according to the characteristics of the substrate.
- Do not apply the product in direct sunlight.

The technical information contained in this sheet is the result of laboratory tests and practical experiences which do not involve any responsibility on our part, as the conditions of use are not under our direct control. In cases of doubt, it is always advisable to ask our technicians for further information regarding the correct application cycle.