



TOP

Washable extra matt

Description	Breathable washable interior paint matt, the product has a good white point and coverage. The final appearance of the product is silky and soft to the touch.
Composition	Based on vinyl resins and selected pigments in water dispersion.
Specific weight medium	1,500-1,550 kg/l Reference standard ISO 2811-1
Surrender	12-14 m ² /l per coat
Percentage by weight of the dry resin on total dryness	10% +/- 1
Coverage	The product has a coverage of 98.7% and therefore falls into <u>CLASS 2</u> Reference standard ISO 6504-3

Class 1	≥ 99.5
Class 2	≥ 98 and < 99.5
Class 3	≥ 95 and < 98
Class 4	< 95

Determination of the resistance to the rubbing wet

After 200 brushing cycles, the product has a loss of thickness of 55 µm and therefore falls within the **CLASS 3 Reference standard ISO 11998**

Brushing resistance	Loss of thickness
Class 1	< 5µm after 200 brushing cycles
Class 2	≥ 5µm and < 20 µm after 200 brushing cycles
Class 3	≥ 20µm and < 70 µm after 200 brushing cycles
Class 4	< 70µm after 40 brushing cycles
Class 5	≥ 70µm after 40 cycles of

	brushing
--	----------

Filling	Good
Movie Look	Opaque
Film thickness	75 - 85 microns in both coats.
Conservation	In a well-closed package
Use	For internal walls
Application	Brush, short-haired roller or spray.
Dilution	Dilute with water 20% - 40%.
Temperature of application	10-35C° max. relative humidity 85%
Drying at 25 C°	Dry: 2 – 4 hours depending on environmental conditions.
Over application	6-8 hours
Color	White
Pack of sale	0.750 lt – 5 lt - 14 lt
Cleaning tools	Water and detergent

Preparation of the support

NEW WALLS:

- Carefully sand and brush the surface to remove any dirt or inconsistencies.
- Apply a coat of acrylic sealer diluted with water.
- Apply two coats of TOP according to the instructions above.

ALREADY PAINTED WALLS:

- Eliminate any inconsistencies in the substrate by carefully brushing and cleaning the substrate.
 - Check the adhesion of old paints, if necessary remove them with the help of a wet sponge, scraper, brush, sandblasting etc.
 - Apply a coat of acrylic sealer diluted with water.
 - Apply two coats of TOP according to the instructions above.
-

SPECIFICATION ITEM (for tenders and estimates)

Description Breathable washable interior paint matt, the product has a good white point and coverage. The final appearance of the product is silky and soft to the touch.

Specific weight
medium 1,500-1.50 kg/l **Reference standard ISO 2811-1**

Determination of the resistance to the rubbing wet After 200 brushing cycles, the product has a loss of thickness of 55 µm and therefore falls within the **CLASS 3 Reference standard ISO 11998**

Coverage The product has a coverage of 98.7% and therefore falls into **CLASS 2 Reference standard ISO 6504-3**.

Percentage by weight of the dry resin on total dryness 10% +/- 1

Warnings

- The temperature of the substrate must be at least 3C° higher than the condensation temperature.
- Apply the product at temperatures ranging from 10C°-35C° and with a relative humidity of max. 85%
- If the product is applied in closed environments, continuous replacement is required of air, so that the water vapors escape.
- Apply the product to a carefully treated surface.
- Yield may vary depending on the characteristics of the support.
- Do not apply the product under direct sunlight.

The technical information provided in this sheet is the result of laboratory tests and practical experiences that do not imply any liability on our part as the conditions of use are not under our direct control. In case of doubt, it is always advisable to ask our technicians for further information regarding the correct application cycle.